

# PAVILAND<sup>®</sup> ARQ RESINA

Microcemento water single-component acrylic background



## DESCRIPTION

Acrylic priming monocomponent, based on resins in watery dispersion indicated for the preparation of the microcement surface before the application of the Paviland Arq Varnish. Fund of preparation of the completion varnish for the systems Paviland Arq.

## COMPOSITION

Product based on acrylic resins in watery base

## FEATURES AND APPLICATIONS

- Improves the adhesion of the varnish of completion of the micro-cement.
- Increases the resistance to the step of liquids along its capacity of sealed.
- Its application is possible between the coat of the micro-cement to improve its adherence and impermeability.
- Its use is adapted to the support in order that the completion varnish could have the gloss degree referred in the specification sheet (although this value will depend also on the smooth completion and on the color of the micro-cement).

## INSTRUCTIONS FOR USE

- The surface must be perfectly hard, structurally in good condition, dry, clean and exempt from fats and waxes
- In case of microcements of high porosity, apply a first coat of Paviland Arq resin diluted with 20% water. Once dry, about 2 hours, but always before 8 hours, lay a second hand undiluted. Once dry the second hand (2 hours approx.), and 8 hours later, apply the Paviland Arq varnish according to the technical data.
- For microcements of reduced porosity (the usual case), apply a single coat of Paviland Arq Resine diluted with 10% water. After 2 or 3 hours and always before the 12 hours, proceed with the laying of the Paviland Arq varnish.

## CAUTIONS AND RECOMMENDATIONS

- Supports must be clean, free of dust, fats, oils, liquids, gratty, etc.
- Do not apply with high humidity, strong wind or frost.
- Do not apply below 10 ° C or above 25 ° C.
- Ensure good ventilation of the room during its application.
- Wear gloves and safety glasses during its application.
- Remains of product should not be poured into rivers, sewers, etc.
- The micro-cement must be completely mature before the application of the Paviland Arq resin.

## PACKAGING

Container 5 L  
Storage up to 1 year in original package closed, sheltered from the weather, humidity and direct sunlight

## NOTE

### TECHNICAL DATA

Usage instructions are made according to our tests and knowledge and do not imply commitment. It doesn't release to the consumer of the examination and verification of products for its correct use. Company's liability shall be limited to the value of the used goods. Claims must be accompanied by original container to allow adequate traceability.

(Statistical results obtained under standard conditions).

Mixture relation	Mono-component
Application temperature	10-25 ° C
Application	8 mm or brush roll
Eventual dilution	10-20% water
Performance	70 - 80 g/m2
Minimum time of repainting	2-3 hours <sup>(1)</sup>
Total dry	12-24 hours <sup>(1)</sup>
Cleaning of tools	Water with the fresh produce

(1) At 20 ° C and 65% R.h.



**SIRIO**  
GROUP

Sirio Group srl

Via D. Corvi 26  
60019 Senigallia (AN) Italy  
Tel. +39 071.65512 Fax. +39 071.7913971  
www.sirio-group.it – info@sirio-group.it