

## MORCEM<sup>®</sup> TEXTURE

One-coat mortar for stamped finish



### DESCRIPTION

One-coat mortar.  
Specially designed for texturing of interior and exterior coatings.  
For hand or pump application directly on the brick.  
Rainwater proof and permeable to water vapour.  
Wide range of decoration possibilities by combination of colours and textures.

### COMPOSITION

Product based on high resistance cement, selected aggregates, special additives, pigments and synthetic resins.

### FEATURES AND APPLICATIONS

- To be applied directly on the brickwork. No need for a previous plastering.
- To be applied indoors and outdoors.
- Waterproof cladding.
- Permeable to water vapour, allowing the substrate to breathe.
- No cracking.
- Wearing resistant. Fading resistant.
- Wide range of decorative finishes by application of molds or rollers.

### SUBSTRATES

- Conventional cement and brickwork based substrates.
- Substrates must be resistant, stable, sound and clean, free of dust, demolding agents, organic products, etc.
- In case of hot or windy weather conditions or when applying over absorbent substrates, it is advisable to wet the substrate and wait until the thin layer of water disappears.
- In particular points (union between different materials, top slabs, pillars, roller blind boxes, angles in the door and window frames, etc.), prepare the mortar with glass fiber mesh to avoid fissures.
- With low-porosity substrates, apply a priming coat (IMPLAFIX) or improve roughness by mechanical means.
- Do not apply on clay or on paint.

### INSTRUCTIONS FOR USE

The stamped one coat mortar requires to follow a series of steps during application which are not very different from conventional rendering jobs.

The steps to be taken are as follows:

- Reinforce the substrate with a mesh on stressed areas and prepare partition joins as in a conventional one-coat system.
- Mix preferably by mechanic means until a homogenous paste is obtained.

### CAUTIONS AND RECOMMENDATIONS

- Spread a layer of 10mm max on the substrate. Thicker coatings can be achieved depending on desired finish texture.
- Wait for 15-20 minutes (depending on weather conditions this may vary) before texturing MORCEM TEXTURE. When the product does not adhere to the naked fingertip it is a good indication that the product is ready to be textured.
- Spray a small quantity of demolding liquid DESMOLDEANTE MORCEM TEXTURE on the render and on the mold/roller. Repeat every 1m2.
- Run the roller on the render to create a pattern. Adequate pressure must be exerted. Hard enough so the stamping is clear but soft enough not to produce pressure waves on the render. Small stamping defects should be fixed immediately during the stamping process.
- Option: 24 hours after application MORCEM TEXTURE can be pigmented by moistening the texture and spreading a dilution of one or many pigments on the stamped render.
- Option: To increase the resistance of the finish, spray RESINA MORCEM TEXTURE on the exiting MORCEM TEXTURE, otherwise use a roller with the lowest yield possible (white foam roller or varnish roller). Apply an even coating so avoiding the generation of straight lines of excess product which may yield a poor finish.

- Do not apply below 5°C nor above 30°C.
- Do not apply when there is a risk of frost, rain, strong wind or direct sunlight.
- It is not advisable to apply on horizontal or sloped surfaces.
- Take care not to contaminate/stain other surrounding elements when spraying RESINA MORCEM TEXTURE

### PACKAGING

25 kg plastic-lined paper bags.  
Shelf life: 1 year in sealed original packaging, sheltered from weather conditions and humidity.

### NOTE

Instructions of use are given based on our testing and knowledge and do not imply any commitment. Said instructions do not free the user from examining and verifying the product for its correct use. The manufacturer's liability is limited to the value of the used goods. Complaints must be accompanied with the original package to allow proper traceability.

### TECHNICAL DATA

(Statistical data obtained under standard conditions)	
Aspect	WHITE or COLOURED powder
Molding time	15-20 min. depending on weather conditions
UNE-EN 998-1 Classification	OC CSIII W2
Approximate yield	18 Kg/m <sup>2</sup> per cm of thickness
Float time	1-2 hours



**SIRIO**  
GROUP

Sirio Group srl

Via D. Corvi 26  
60019 Senigallia (AN) Italy  
Tel. +39 071.65512 Fax. +39 071.7913971  
www.sirio-group.it – info@sirio-group.it